

## Transparent Matt Write & Erase Overlamine - TAG Digital®



### TECHNICAL DATA SHEET

#### Description:

The **Transparent Matt Write & Erase Overlamine - TAG Digital®** is designed to be used as an erasable writing surface with dry erase markers such as Velleda, in classrooms, meeting rooms and other professional environments. It can also be used as an anti-graffiti protective lamination for printed surfaces.

#### Characteristics:

The **Transparent Matt Write & Erase Overlamine - TAG Digital®** is composed of a 55 µm ultra-clear PET film with a matt surface finish, coated with a solvent-based permanent transparent adhesive.

The matt surface reduces reflections and provides a smooth writing finish, allowing repeated writing and erasing without leaving marks. The product is not suitable for printing.

It is protected by a PE-coated paper liner, ensuring good handling and easy application.

#### Durability:

The maximum recommended duration of use is 3 years.

#### Storage:

1 year when stored between 15°C and 25°C and at a relative humidity of 45 to 55% in the original packaging.

#### Adhesion:

Adhesive strength 180° (FTM 1): 9 N/25 mm +/- 1N/25 mm

Initial adhesion (FTM9): 6 N/25 mm +/- 1N/25 mm

Final adhesion after 24 hours.

Adhesion temperature: 15° to 40° C

Temperature of use: -20°C to 60° C

#### Product references:

|  |                    |                        |
|--|--------------------|------------------------|
| <b>Transparent Matt Write &amp; Erase Overlamine</b> | <b>1.25 x 50 m</b> | ERASE-PET-TM-55-125050 |
|--|--------------------|------------------------|

Note:

The information in this data sheet is based on laboratory tests and experience gained in practice. It does not constitute a legal guarantee. A test prior to use must be carried out.

Durability is estimated based on exposure conditions in Central Europe. The actual life of the product depends on substrate preparation, exposure conditions and maintenance of the marking. Outdoor performance degradation can be expected when the films are exposed southward, if applied in areas with high temperatures such as Southern European countries, or in polluted areas.